



Typ SVG



PRODUCT INFORMATION

The SVG conduit couplings are made of specially modified polyamide 6. The material is halogen, phosphor and cadmium-free. The conduit couplings are used as an extension or for the repair of cable protection conduits and feature the following advantages:

- Easy assembly by latching
- Split version makes routing of cables easy
- Can also be screwed on


SPECIFICATIONS

	mod. polyamide PA 6
	-40 – 110 °C short term 140 °C
	IP42 IP54 bolted
	acc. to UL94 V0 self-extinguishing
	C.I.T. R22 / R23 HL3 = 00:43 LOI R22 / R23 HL3 = 33,8 % Ds (max.) R22 / R23 HL3 = 63



Article	Order No.	Colour	Suitable for Murrflex	A mm	B mm	C mm	G mm	MOQ pcs.
SVG 21	83701630	Black	M25/P21(S)	31.00	36.00	50.00	5.50	25
SVG 29	83701632	Black	M32/P29(S)	36.80	44.00	54.00	5.50	25
SVG 36	83701634	Black	M40/P36(S)	44.80	50.00	66.00	5.50	10
SVG 48	83701636	Black	M50/P48(S)	56.80	64.00	66.00	5.50	10
SVG 21	83701610	Gray	M25/P21(S)	31.00	36.00	50.00	5.50	25
SVG 29	83701612	Gray	M32/P29(S)	36.80	44.00	54.00	5.50	25
SVG 36	83701614	Gray	M40/P36(S)	44.80	50.00	66.00	5.50	10
SVG 48	83701616	Gray	M50/P48(S)	56.80	64.00	66.00	5.50	10

MATERIAL PROPERTIES



THERMAL PROPERTIES



PROTECTION CLASS



Typ SVG

FIRE PROPERTIES



acc. to UL94 V0 self-extinguishing



Fire properties as per EN 45545-2

C.I.T. R22 / R23 HL3 = 00:43

LOI R22 / R23 HL3 = 33,8 %

Ds (max.) R22 / R23 HL3 = 63

TECHNICAL INFORMATION



Halogen-free

CONFORMITY



RoHS (EC Directive 2011/65/EU)

APPROVALS AND OPERATING PERMITS



EU railway approval

EN 45545-2 R22/R23 3x HL3

GENERAL INFORMATION



Made in Germany

All details given in our sales brochures and catalogues, as well as the information available online, are based on our current knowledge of the products described.

The electronic data and files made available by Murrplastik, particularly CAD files are based on our current knowledge of the product described.

A legally binding assurance of certain properties or the suitability for a certain purpose can not be determined from this information.

All information with respect to the chemical and physical properties of Murrplastik products, as well as application advice given verbally, in writing or by tests, is given to the best of our knowledge.

They do not release the buyer from the obligation to carry out his own tests and trials in order to determine the concrete suitability of the products for the intended purpose.

Murrplastik accepts no responsibility for the available information being up-to-date, correct or complete. Neither do we accept responsibility for the quality of this information.

Murrplastik accepts no liability for damage caused as a result of using our products.

Murrplastik reserves the right to make technical changes and improvements through constant further development of products and services.

Our General Terms and Conditions apply.

© Murrplastik Systemtechnik GmbH • proID_65882~20220317~890283~suv_svg