



Type EWX-PA-LS (high corrugation)



PRODUCT INFORMATION

The EWX-PA-LS cable protection conduits are made of specially modified polyamide 6. The material is halogen, phosphor and cadmium-free. For installation of pre-assembled cables, retrofitting or repair of cables. For static applications involving extreme mechanical loads.

The EWX-PA-LS cable protection conduits have a higher corrugation and feature the following advantages:

- Good flexibility
- Less wear
- Excellent crush resistance
- Subsequent installation possible

SPECIFICATIONS

	Mod. polyamide PA 6
	According to IEC EN 61386 Cycles: > 13000 ~
	-40 – 120 °F Short periods 160 °F
	acc. to UL94 HB

Article	Order No.	Color	A Ø mm	B Ø mm	R stat. mm	Weight lbs/100ft	MOQ m
EWX-PA-LS M25/P21	83163058	Black	19.80	28.10	49.00	10.50	50
EWX-PA-LS M32/P29	83163060	Black	24.10	34.50	57.00	12.70	25
EWX-PA-LS M40/P36	83163062	Black	29.70	42.10	71.00	20.50	25
EWX-PA-LS M50/P48	83163064	Black	38.00	54.10	87.00	23.00	25

MATERIAL PROPERTIES



Mod. polyamide PA 6



Flexural fatigue strength

Cycles: > 13000 ~; Testing method: According to IEC EN 61386

THERMAL PROPERTIES



Temperature / temperature range

-40 – 120 °F Short periods 160 °F

FIRE BEHAVIOR



acc. to UL94 HB

TECHNICAL INFORMATION



Halogen-free

DIN 53474

Type EWX-PA-LS (high corrugation)

CONFORMITY

 **RoHS (EC Directive 2011/65/EU)**

APPROVALS AND OPERATING PERMITS

 **F&E/P3-ENr. 40-1**

GENERAL INFORMATION

 **Made in Germany**

All details given in our sales brochures and catalogs, as well as the information available online, are based on our current knowledge of the products described.

The electronic data and files made available by Murrplastik, particularly CAD files are based on our current knowledge of the products described.

A legally binding assurance of certain properties or the suitability for a certain purpose can not be determined from this information.

All information regarding the chemical and physical properties of Murrplastik products, as well as application advice given verbally, in writing or in experiments, is given to the best of our knowledge.

This does not free the purchaser of carrying out their own inspections and tests in order to determine the suitability of a product for a specific purpose.

Murrplastik accepts no responsibility for the available information being up-to-date, correct or complete. Neither do we accept responsibility for the quality of this information.

Murrplastik accepts no liability for damage caused as a result of using our products.

Murrplastik reserves the right to make technical changes and improvements through constant further development of products and services.

Our General Terms and Conditions apply.

© Murrplastik Systemtechnik GmbH • proID_64739~20220201~890283~suv_ewxpals